

TECHNICAL DATA SHEET

6511

BROMOBUTYL CAP STRIP

February 2, 2012

Polycorp 6511 is a 50A durometer "Pure" bromobutyl (halobutyl) rubber lining used for stripping butt joints on bromobutyl 6512.

Application Notes:

- **Skive** – Open skive construction.
- **Repair** – Same
- **Cured Durometer** – Shore A Durometer of top surface: 50 ± 5.
- A heated table to warm the rubber to 110–120°F (43°C) is recommended
- **Spark Test** – Refer to section 13 of the Application Manual

Adhesive Notes:

See Section 9 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes.

For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C).

Use adhesives in well ventilated area and always consult the material safety data sheet for specific precautions.

<u>Coat</u>	<u>Polycorp Adhesive</u>	<u>Approved Equivalent</u>
1 st Coat on Metal	N/A	N/A
2 nd Coat on Metal	N/A	N/A
3 rd Coat on Metal	N/A	N/A
4 th Coat on lining	N/A	N/A

For distributors of Chemlok adhesives, see Section 9 of the Application Manual

Curing:

Cure time adjustments may be required to compensate for specific conditions. See Section 11 of the Application Manual for detailed instructions.

Autoclave Method – Up to 1/4" thickness:

2 hours @ 292°F/144°C (45 psi).

Internal Steam Method – Up to 1/4" thickness:

8 hours @ 260°F/127°C (20 psi).

Atmospheric Steam Method – Up to 1/4" thickness:

Minimum 30 hours @ 212°F/100°C

Storage:

Store in a cool, dry area.

Shelf Life:

Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	60 days
Stored between 71 and 90°F	30 days
Do not store above 90°F (32°C)	

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual

TECHNICAL DATA SHEET

6511 Page 2 of 2

Typical Properties:

<u>Property</u>	<u>Value</u>	<u>ASTM Test Method</u>
Hardness (Face)	50 A \pm 5	D2240
Tensile Strength (min, psi)	1200	D412
Elongation at Break (min, %)	400 %	D412
Specific Gravity	1.21	D927
Adhesion to Metal (min, lbs)	25	D429
Maximum Operating Temperature for Optimum Service Life	127°C/ 260°F	N/A

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.

PRECAUTIONS:

- Joints can be made using either a lap or closed skive construction.
- Swab mating surfaces of cap strip and lining with toluol solvent. **Do not use cement on cap strips.**
- **Preheat cap strip for at least 10 minutes on a 120°F/43°C heat table.** Thoroughly stitch edges of cap strip so edges are completely sealed.