

TECHNICAL DATA SHEET

1036 Page 1 of 2

1036

SEMI-HARD FLEXIBLE RUBBER

October 1, 2010

Polycorp 1036 is a black 85 A durometer (35 D) combination of natural rubber and synthetic materials with or without soft natural rubber tie gum. Excellent chemical resistance at elevated temperature. FDA compliant as per 21CFR177.2600. A-I-E cure.

Application Notes:

- **Skive** – use closed skive construction
- **Repair** – Same
- **Cured Durometer** – Shore A Durometer of top surface: 85 ± 10. Shore D Durometer of top surface: 35 ± 10.
- **Spark Test** – Refer to section 13 of the Application Manual

Adhesive Notes:

See Section 9 of the Polycorp Rubber Lining Application Manual for specific cementing / adhesion notes.

For proper adhesion, temperatures must be over 60°F (15°C) and must not exceed 120°F (49°C).

Use adhesives in well ventilated area and always consult the material safety data sheet for specific precautions.

<u>Coat</u>	<u>Polycorp Adhesive</u>	<u>Approved Equivalent</u>
1 st Coat on Metal	C-90 Primer	Chemlok 289
2 nd Coat on Metal	C-91 Intermediate	Chemlok 290
3 rd Coat on Metal	C-202S Tack	Chemlok 286
4 th Coat on lining	C-202S Tack	Chemlok 286

For distributors of Chemlok adhesives, see Section 9 of the Application Manual

Curing:

Cure time adjustments may be required to compensate for specific conditions. See Section 11 of the Application Manual for detailed instructions.

Autoclave Method – 3/16” & 1/4” thickness:
3 hours @ 260°F/127°C (20 psi) .

Internal Steam Method – 3/16” & 1/4” thickness: 6 hours @ 267°F/131°C (20 psi).

Atmospheric Steam Method - Up to 1/4” thickness: Minimum 30 hours @ 212°F /100°C
Lower durometer readings may result with this type cure.

Storage:

Store in a cool, dry area.

Shelf Life:

Stored below 50°F (10°C)	180 days
Stored between 51 and 70°F	60 days
Stored between 71 and 90°F	30 days
Do not store above 90°F (32°C)	

Storage, handling and application methods must conform to the Polycorp Rubber Lining Application Manual

TECHNICAL DATA SHEET

1036 Page 2 of 2

Typical Properties:

Property	Value	ASTM Test Method
Hardness (Face)	85 A/ 35D ± 10	D2240
Tensile Strength (min, psi)	1000	D412
Elongation at Break (min, %)	50%	D412
Specific Gravity	1.18	D927
Adhesion to Metal (min, lbs)	25	D429
Maximum Operating Temperature for Optimum Service Life	93°C/ 200°F	N/A

All physical property values developed and measured using a press-cured sample sheet prepared in accordance with ASTM D3182.

PRECAUTIONS:

- This is a hard rubber compound. Overcure will cause brittleness.
- Do not use in transport equipment or tanks to be installed outside.
- This lining may not be suitable for equipment that may be exposed to extremely low temperatures. If temperatures will be below 32 °F/0 °C, contact Polycorp with all the service conditions for a specific recommendation.
- Cool down to 120 °F/49 °C before releasing pressure during pressure cure.
- Do not ship lined tank below 20 °F